

50 X 50 SQ					√	√	√	√	√	√	√	√	√	√	√	√			
25 X 12 RECT	√	√	√	√	√	√	√	√	√	√	√	√	√						
30 x 20 RECT		√	√	√	√	√	√	√	√	√	√	√	√	√	√				
40 x 20 RECT		√	√	√	√	√	√	√	√	√	√	√	√	√	√	√			
40 x 25 RECT			√	√	√	√	√	√	√	√	√	√	√	√	√				
40 X 30 RECT			√	√	√	√	√	√	√	√	√	√	√	√	√				
50 x 20 RECT			√	√	√	√	√	√	√	√	√	√	√	√	√				
50 x 25 RECT			√	√	√	√	√	√	√	√	√	√	√	√	√	√			
30 X 50 RECT				√	√	√	√	√	√	√	√	√	√	√	√				
60 x 30 RECT					√	√	√	√	√	√	√	√	√	√	√	√			
60 X 40 RECT					√	√	√	√	√	√	√	√	√	√	√	√			
33 x 13 OVAL	√	√	√	√	√	√	√	√	√	√	√	√	√	√	√				
35 x 15 OVAL		√	√	√	√	√	√	√	√	√	√	√	√	√	√				
24 X 33 OVAL			√	√	√	√	√	√	√	√	√	√	√	√	√				
40 x 20 OVAL			√	√	√	√	√	√	√	√	√	√	√	√	√				
59 x 30 OVAL				√	√	√	√	√	√	√	√	√	√	√	√	√			
40 X 22 ELIP			√	√	√	√	√	√	√	√	√	√	√	√	√				
<div style="display: flex; justify-content: space-between; align-items: center;"> √ Non Fincut only √ Both Fincut & Non Fincut </div>																			

New Grade Manufacturing									
Raw Material Grade	Thickness	Yield Strength (Mpa Min.)			Ultimate Tensile Strength (Mpa Min.)			% Elongation (min.) GL=5.65	
High Strength Micro-Alloy Grade 2	2.50 MM	470			540			10%	
High Strength Micro-Alloy Grade 2	2.00 MM	470			540			10%	
High Strength Micro-Alloy Grade 3	1.20 MM 1.50 MM 1.60 MM	500			600			10%	
Raw Material Grade	Thickness	% C	% Mn	% Si	% S(max.)	% P(max.)	% Ti (min.)	% V(min.)	% Nb (min.)
High Strength Micro-Alloy Grade 2	2.50 MM	0.20 max.	0.5 -1.5	0.35 max.	0.04	0.04	0.01	0.015	0.01
High Strength Micro-Alloy Grade 2	2.00 MM	0.20 max.	0.5 -1.5	0.35 max.	0.04	0.04	0.01	0.015	0.01
High Strength Micro-Alloy Grade 3	1.20 MM 1.50 MM 1.60 MM	0.20 max.	0.5 -1.8	0.35 max.	0.04	0.04	0.01	0.015	0.01